



Pavestone UK Limited
Burford Quarry, Burford Road
Brize Norton, Oxfordshire.
OX18 3WN

13

EN 1341 : 2012
Indian Sandstone – Tudor Antique Cloister

Pavestone Indian Sandstone Flags are intended for use in and around domestic dwellings as a paving material suitable for home patios, pathways and internal floor coverings. Pavestone Indian Sandstone Flags are not designed for vehicular trafficking or for commercial properties.

	Test Results	Protocol
Flexural Strength (MPa)	34.8 (mean)	EN – 12372:2006
Frost Resistance Flexural Strength after 48 cycles freeze/ thaw (MPa)	32.8 (mean)	EN – 12372:2006 EN – 12371:2001
Compressive Strength (kg/cm ²)	565.4 (mean)	EN – 12372:2006
Slip / Skid Resistance – Dry	74 (mean)	EN – 14231:2003
Slip / Skid Resistance – Wet	60 (mean)	EN – 14231:2003
Durability – Resistance to wear (mm)	6.2 (mean)	EN – 14157:2004
Water Absorption by wt (%)	0.42 (mean)	EN – 13755:2001
Release of dangerous substances	NPD	

Manufactured in Kota, Rajasthan. India